

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 0 987 166 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication: 22.03.2000 Bulletin 2000/12

(21) Application number: 99118288.2

(22) Date of filing: 15.09.1999

(51) Int. CI.⁷: **B62D 21/11**, B60G 7/00, B21D 39/02, B21D 53/88, C22C 38/00, C22C 38/42

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE

Designated Extension States: AL LT LV MK RO SI

(30) Priority: 16.09.1998 IT TO980785

(71) Applicant: M.A.C. S.p.A. 10044 Pianezza (Torino) (IT) (72) Inventor: Azzolini, Ezio 10090 Sangano (Torino) (IT)


(74) Representative:

Fioravanti, Corrado et al Jacobacci & Perani S.p.A. Corso Regio Parco 27 I-10152 Torino (IT)

(54) A structural element for a motor vehicle

(57) A structural element for a motor vehicle, in particular, a frame (10) for supporting an engine and suspension units, is described. Two pressed sheet-steel half-shells (11, 12) with concave cross-sections are fitted together with their concave sides facing one another

to define a closed cross-section and are fixed together along respective outwardly-projecting peripheral rims (13, 14). The half-shells are connected by seaming of their rims (13, 14).



besonplion

[0001] The present invention relates to a structural element for a motor vehicle and, in particular, to a frame for supporting an engine and suspension units, of the type comprising a pair of pressed sheet-steel half-shells with concave cross-sections fitted together along a given axis with their concave sides facing one another to define a closed cross-section and fixed together along respective peripheral rims projecting outwardly and perpendicular to the given axis.

[0002] At the moment, the two superimposed halfshells of structural elements of this type are arranged for automatic welding by continuous seam welding along the perimeters of the half-shells.

[0003] The joining of the half-shells by welding has a first disadvantage owing to the fact that the welding often has non-homogeneous portions which require localized re-welding which is not always accepted by the vehicle manufacturer.

[0004] Moreover, the welds comprise minute cracks which, in time, may lead to localized breakages due to the dynamic stresses to which the structural element is subjected, particularly if it is a frame for supporting the engine and suspension units. In addition, the minute cracks in turn represent critical regions for corrosion.

[0005] Finally, the welding process is difficult to control from a qualitative point of view without considerable investment in control equipment.

[0006] The object of the present invention is to provide a load-bearing structural element for a motor vehicle which can prevent the problems mentioned above and which can be produced by a method of manufacture which leads to a reduction in costs in comparison with conventional solutions which provide for welding of the half-shells.

[0007] This object is achieved, according to the present invention, by means of a structural element of the type identified in the introductory portion of the description, characterized in that the half-shells are connected by seaming of their rims.

[0008] Further characteristics and advantages of the present invention will become clear in the course of the detailed description of an embodiment thereof, given with reference to the appended drawings provided by way of non-limiting example, in which:

Figure 1 is a general perspective view of a frame according to the present invention for supporting the engine and suspension units of a motor vehicle, and

Figure 2 is a cross-section taken on the line II-II of Figure 1, on an enlarged scale.

[0009] With reference initially to Figure 1, a structural element according to the present invention is generally indicated 10; in this embodiment, the structural element

units of a motor vehicle.

[0010] As also shown in Figure 2, the frame 10 is formed by joining together a pair of pressed sheet-steel half-shells 11, 12 having concave cross-sections. The two half-shells 11, 12 are fitted together and juxtaposed along an axis defined herein as vertical, with their concave sides facing one another so as jointly to define a closed cross-section (Figure 2).

[0011] The two half-shells 11, 12 have respective peripheral rims 13, 14 which project outwardly and horizontally; the rims 13 of the upper half-shell 11 have a width approximately twice that of the rims 14 of the lower half-shell 12 so that they can be turned over in a U-shaped arrangement around and beneath the rims 14 by a seaming operation, starting from an initial undeformed condition, indicated 13', in which these rims are initially straight.

[0012] The upper half-shell 11 is made of a sheet steel having a thickness s_1 which is less than the thickness s_2 of the sheet constituting the lower half-shell 12. This facilitates the bending of the rim 13 to be turned over; moreover, as can be understood from an observation of Figure 2, this configuration prevents water from collecting in the vicinity of the coupling rims since the end 13a of the rim 13 acts as a dripper for any water deposited on the outside of the upper half-shell 11.

[0013] The sheets used to form the half-shells 11, 12 and, in particular, the upper half-shell 11, the edge of which is bent into a U-shape, are made of a special high-strength steel such as, for example, that marketed by the firm Sollac with the reference DP 600. The use of this steel enables the thicknesses of the sheets to be reduced.

[0014] A steel of this type has the following chemical composition (% by weight):

C ≤ 0.100 Mn ≤ 0.800

5

10

15

20

25

30

40

50

55

P from 0.060 to 0.090

S ≤ 0.008

Si ≤ 450

Cu from 0.250 to 0.550

Ni ≤ 0.350

Cr from 0.450 to 0.650

[0015] With regard to the dimensions of the rims of a structural element which, as in the embodiment illustrated, has the functions of a front frame for supporting an engine and suspension units, the rims 14 of the lower half-shell 12 preferably have a width of between about 7 and about 9 mm which enables the two half-shells to be joined together firmly and renders the element composed thereof easily able to withstand the dynamic stresses to which such frames are normally subjected.

[0016] The seaming of the half-shells is performed substantially continuously along their peripheries,

10

15

25

30

4

except for the points at which one of the two half-shells forms projecting portions such as, for example, those indicated 15, to constitute means for fixing to other parts and components of the motor vehicle.

[0017] Naturally, the principle of the invention remaining the same, the forms of embodiment and details of construction may be varied widely with respect to those described and illustrated purely by way of non-limiting example, without departing from the scope of the invention as defined in the appended claims.

Claims

- A structural element for a motor vehicle, in particular, a frame (10) for supporting an engine and suspension units, of the type comprising a pair of pressed sheet-steel half-shells (11, 12) with concave cross-sections fitted together along a given axis with their concave sides facing one another to define a closed cross-section and fixed together along respective peripheral rims (13, 14) projecting outwardly and perpendicular to the given axis, characterized in that the half-shells are connected by seaming of the rims (13, 14).
- A structural element according to Claim 1, characterized in that the rims (13) of a first (11) of the half-shells are turned over onto the rims (14) of the second (12) of the half-shells.
- A structural element according to Claim 1, of the type in which one, upper half-shell (11) is superimposed vertically on the other, lower half-shell (12), characterized in that the rims (13) of the upper halfshell (11) are turned over around and beneath the rims (14) of the lower half-shell (12).
- 4. A structural element according to Claim 1, characterized in that the first half-shell (11), the rims (13) of which are turned over, is made of sheet metal having a thickness (s1) less than the thickness (s2) of the sheet steel constituting the second half-shell (12).
- 5. A structural element according to Claim 1, characterized in that at least the first half-shell (11) is made of a steel which has the following chemical composition (% by weight):

C ≤ 0.100 Mn ≤ 0.800

P from 0.060 to 0.090

S ≤ 0.008 Si ≤ 450

Cu from 0.250 to 0.550


Ni ≤ 0.350


Cr from 0.450 to 0.650

- 6. A structural element according to Claim 4, characterized in that the sheet-steel constituting the first half-shell (11) has a thickness of about 1.5 mm and in that the sheet-steel constituting the second half-shell (12) has a thickness of about 2 mm.
- A structural element according to Claim 1, characterized in that the rim (14) of the second half-shell (12) has a width of between about 7 and about 9 mm, measured in a direction perpendicular to that in which the rim (14) extends.
- 8. A structural element according to Claim 1, characterized in that the seaming is performed substantially continuously along the peripheries of the two half-shells (11, 12).

50

55







EUROPEAN SEARCH REPORT

Application Number EP 99 11 8288

| Category | | lication, where appropriate, | Relevant | CLASSIFICATION OF THE | | |
|------------------------|---|---|---|------------------------|--|--|
| | of relevant passa | | to claim | APPLICATION (Int.CI.7) | | |
| Χ | | RISCHE MOTOREN WERKE | 1 | B62D21/11 | | |
| | AG) 28 February 1991 | | - | B60G7/00 | | |
| Y | * the whole document | * | 2 | B21D39/02 B21D53/88 | | |
| Y | DE 26 59 081 A (VOLK 6 July 1978 (1978-07 * the whole document | -06) | 1,2 | C22C38/00 C22C38/42 | | |
| Y | DE 31 09 565 A (DAIM 14 October 1982 (198 * the whole document | 2-10-14) | 1,2 | | | |
| X | FR 1 292 680 A (DAIM 28 September 1962 (1 * the whole document | 962-09-28) | 1 | | | |
| Y | DE 10 74 416 B (DAIM 28 January 1960 (196 * the whole document | 0-01-28) | 1,2 | | | |
| Y | PATENT ABSTRACTS OF vol. 014, no. 203 (M 25 April 1990 (1990- & JP 02 041724 A (NI 9 February 1990 (1991) * abstract; figures | 1,2 | TECHNICAL FIELDS SEARCHED (Int.Cl.7) B62D B60G B21D C22C | | | |
| Y | PATENT ABSTRACTS OF vol. 008, no. 032 (M 10 February 1984 (19 & JP 58 188712 A (NI KK;OTHERS: 01), 4 November 1983 (198 * abstract; figure 9 | 1,2 | | | | |
| | The present search report has b | een drawn up for all claims | | | | |
| Place of search | | Date of completion of the search | l l | Examiner | | |
| | THE HAGUE | 6 December 199 | 9 T | sitsilonis, L | | |
| X : pa Y : pa do | CATEGORY OF CITED DOCUMENTS inticularly relevant if taken alone inticularly relevant if combined with anoth ocument of the same category chnological background | E : earlier pater after the film er D : document c L : document ci | ited in the applicati ted for other reaso | ublished on, or ion | | |

5

EUROPEAN SEARCH REPORT

EP 99 11 8288

| ategory | Citation of document with income of relevant passa | dication, where appropriate, | Relevant to claim | CLASSIFICATION OF THE APPLICATION (Int.CI.7) |
|---------------------------|--|--|---|--|
| A | DE 195 35 870 A (BLZ LASERZENTRUM G) 6 February 1997 (199 * column 1, line 1 - 1,2,5,8 * * column 7. line 55 | BAYERISCHES | 1,4 | |
| A | PATENT ABSTRACTS OF vol. 012, no. 031 (N 29 January 1988 (198 & JP 62 184976 A (N) 13 August 1987 (1987 * abstract * | M-663), 38-01-29) ISSAN MOTOR CO LTD), | 1-3 | |
| Α | PATENT ABSTRACTS OF vol. 017, no. 100 (0 26 February 1993 (19 & JP 04 289122 A (NI 14 October 1992 (1994) * abstract * | C-1030), 993-02-26) KK CORP), | 5 | TECHNICAL FIELDS SEARCHED (Int.Cl.7) |
| A | DE 35 40 520 A (VOL) 5 June 1986 (1986-0 | | | |
| A | PATENT ABSTRACTS OF vol. 006, no. 172 (7 September 1982 (1 & JP 57 084267 A (M 26 May 1982 (1982-0 * abstract; figures | M-154), 982-09-07) AZDA MOTOR CORP), 5-26) | | |
| | | | - | |
| | The present search report has | | | |
| | Place of search | Date of completion of the seam | | Examiner |
| | THE HAGUE | 6 December 19 | yy Is | itsilonis, L |
| Y:po do A:te O:n | CATEGORY OF CITED DOCUMENTS articularly relevant if taken alone articularly relevant if combined with and ocument of the same category ichnological background on-written disclosure termediate document | E : earlier pate after the fill ther D : document L : document | rinciple underlying the int document, but put ing date cited in the application cited for other reason the same patent fam | oilshed on, or on s |

EP 0 987 166 A1

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 99 11 8288

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06-12-1999

| Patent document cited in search report | | Publication date | Patent family member(s) | Publication date |
|--|---|------------------|-------------------------------|---|
| DE 3927987 | Α | 28-02-1991 | NONE | * ************************************* |
| DE 2659081 | Α | 06-07-1978 | BR 7708622 A | 22-08-1978 |
| DE 3109565 | Α | 14-10-1982 | NONE | |
| FR 1292680 | Α | 28-09-1962 | CH 384375 A DE 1144123 B | |
| DE 1074416 | В | | NONE | |
| JP 02041724 | Α | 09-02-1990 | NONE | |
| JP 58188712 | Α | 04-11-1983 | NONE | |
| DE 19535870 | Α | 06-02-1997 | NONE | |
| JP 62184976 | Α | 13-08-1987 | NONE | |
| JP 04289122 | Α | 14-10-1992 | JP 2745823 B | 28-04-1998 |
| DE 3540520 | Α | 05-06-1986 | NONE | |
| | | 26-05-1982 | JP 1448704 C JP 62060309 B | 11-07-1988 15-12-1987 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

FORM P0459

THIS PAGE BLANK (USPTO)